

## REPORT DOCUMENTATION PAGE

Form Approved  
OMB No. 0704-0188

The reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

1. AGENCY USE ONLY (Leave blank)

2. REPORT DATE

January 1991

3. REPORT TYPE AND DATES COVERED

Final Report 10/1/86-09/3090

4. TITLE AND SUBTITLE

Structure and Properties of Novel Compounds of  
Silicon, Germanium and Tin

5. FUNDING NUMBERS

61102F 2303 B2

6. AUTHOR(S)

7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)

University of Texas  
P.O. Box 7726  
Austin, TX 78713-77268. PERFORMING ORGANIZATION  
REPORT NUMBER

AEOSR-TR

91 0173

9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)

AFOSR/NC  
Building 410, Bolling AFB, DC  
20332-644810. SPONSORING/MONITORING  
AGENCY REPORT NUMBER

AFOSR-87-0001

11. SUPPLEMENTARY NOTES

DTIC  
ELECTE  
S B D  
MAR 13 1991

12a. DISTRIBUTION/AVAILABILITY STATEMENT

APPROVED FOR PUBLIC RELEASE; DISTRIBUTION IS UNLIMITED.

12b. DISTRIBUTION CODE

13. ABSTRACT (Maximum 200 words)

We have concentrated our efforts on the spectroscopy, photophysics, and photochemistry of polysilanes, using a combination of experimental and theoretical tools. We have developed a more detailed version of the chain segment model, have identified and thoroughly characterized the persistent radical formed in UV photolysis, documented further the recently uncovered process of photoinduced chain scission by reductive elimination, and advanced the theoretical understanding of the electronic states of model short-chain oligosilanes. The combined results suggest strongly that the shorter chromophoric chain segments have a different lowest excited singlet state (on\*) than the longer ones (oo\*). Confirming evidence for this is still being sought.

14. SUBJECT TERMS

15. NUMBER OF PAGES

16. PRICE CODE

17. SECURITY CLASSIFICATION  
OF REPORT

UNCLASSIFIED

18. SECURITY CLASSIFICATION  
OF THIS PAGE

UNCLASSIFIED

19. SECURITY CLASSIFICATION  
OF ABSTRACT

UNCLASSIFIED

20. LIMITATION OF ABSTRACT

AD-A232 892

Technical Report

STRUCTURE AND PROPERTIES OF NOVEL  
COMPOUNDS OF SILICON, GERMANIUM AND TIN

The Air Force Office of Scientific Research  
Air Force Systems Command

Contract No. 87-0001

Principal Investigator

Josef Michl  
Center for Structure and Reactivity  
Department of Chemistry  
The University of Texas  
Austin, TX 78712-1167

Period Covered: October 1, 1989 - September 30, 1990

## ABSTRACT

We have concentrated our efforts on the spectroscopy, photophysics, and photochemistry of polysilanes, using a combination of experimental and theoretical tools. We have developed a more detailed version of the chain segment model, have identified and thoroughly characterized the persistent radicals formed in UV photolysis, documented further the recently uncovered process of photoinduced chain scission by reductive elimination, and advanced the theoretical understanding of the electronic states of model short-chain oligosilanes. The combined results suggest strongly that the shorter chromophoric chain segments have a different lowest excited singlet state ( $\sigma\pi^*$ ) than the longer ones ( $\sigma\sigma^*$ ). Confirming evidence for this is still being sought.

Accession For	
NTIS GRA&I	<input checked="checked" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A-1	



**Lectures Given Which Acknowledge Support of AFOSR 87-0001**

4th International Conference on Unconventional Photoactive Solids, San Jose,  
CA

University of Santiago, Santiago, Chile

XXIII Organosilicon Symposium, Midland, MI

Symposium on "Key Problems in Silicon Chemistry", University of Colorado,  
Boulder, CO.

13th IUPAC Symposium on Photochemistry, University of Warwick, Coventry,  
England

200th ACS National Meeting, Symposium on Sigma-Conjugated Polymers (ACS/APS  
jointly sponsored), Washington, DC

The following individuals participated in the work:

Allan McKinley

V. Balaji

Ya-Ping Sun

Juliusz G. Radziszewski

CUMULATIVE LIST OF PUBLICATIONS WHICH ACKNOWLEDGE SUPPORT OF AFOSR 87-0001

A. Publications previously reported:

1. Michalczyk, M. J.; Fink, M. J.; Haller, K. J.; West, R.; Michl, J. "Structural and Chemical Properties of 1,3-Cyclodisiloxanes", *Organometallics* 1986, 5, 531.
2. Michalczyk, M. J.; Fink, M. J.; De Young, D. J.; Carlson, C. W.; Welsh, K. M.; West, R.; Michl, J. "Organosilylenes and their Dimerization to Disilenes", *Silicon, Germanium, Tin, and Lead Compounds* 1986, 9, 75.
3. Vančik, H.; Raabe, G.; Michalczyk, M. J.; West, R.; Michl, J. "Dimethylsilylene: A Trisilane and a Geminal Diazide as New Photochemical Precursors. Evidence for an Absorption Maximum Near 450 nm", *J. Am. Chem. Soc.* 1985, 107, 4097.
4. Weeks, G. H.; Adcock, W.; Klingensmith, K. A.; Waluk, J. W.; West, R.; Vasak, M.; Downing, J.; Michl, J. "A Probe for Substituent Hyperconjugative Power: Magnetic Circular Dichroism of the Benzene  $L_p$  Band", *Pure Appl. Chem.* 1986, 58, 39.
5. Raabe, G.; Vančik, H.; West, R.; Michl, J. "IR Transition Moment Directions in Matrix-Isolated Dimethylsilylene and 1-Methylsilene", *J. Am. Chem. Soc.* 1986, 108, 671.
6. Zigler, S. S.; West, R.; Michl, J. "Observation of a Silanimine in an Inert Matrix and in Solution at Low Temperature", *Chem. Lett.* 1986, 1025.
7. Sekiguchi, A.; Zigler, S. S.; West, R.; Michl, J. "Synthon for the Silicon-Silicon Triple Bond", *J. Am. Chem. Soc.* 1986, 108, 4241.
8. Zigler, S. S.; Welsh, K. M.; West, R.; Michl, J. "Matrix Isolation of the First Silanediimine, N,N'-Bis(trimethylsilyl)silanediimine", *J. Am. Chem. Soc.* 1987, 109, 4392.
9. Welsh, K. M.; Rich, J. D.; Michl, J.; West, R. "The Generation of Hexamethyl-1,4-Disilabenzene and Its Novel Thermal Chemistry", *J. Organomet. Chem.* 1987, 325, 105.
10. DeYoung, D. J.; Fink, M. J.; West, R.; Michl, J. "The Addition Reactions of Two Disilenes", *Main Group Metal Chemistry* 1987, 10, 19.
11. Raabe, G.; Michl, J. "Multiple Bonding to Silicon", *Chem. Rev.* 1985, 85, 419.
12. Welsh, K. M.; Michl, J.; West, R. "The Photochemistry of Matrix-Isolated Di-*tert*-butyldiazidosilane. Observation of Di-*tert*-butylsilylene and N,N'-Di-*tert*-butylsilanediimine", *J. Am. Chem. Soc.* 1988, 110, 6689.
13. Raabe, G.; Michl, J. "Multiple Bonds to Silicon", in "The Chemistry of Organic Silicon Compounds", Patai, S.; Rappoport, Z., Eds., John Wiley & Sons Ltd.: Chichester, 1989, Chapter 17, 1015.

B. Publication previously reported as in Press or Submitted that have now appeared:

14. Barrau, J.; Bean, D. L.; Welsh, K. M.; West, R.; Michl, J. "Photochemistry of a Matrix-isolated Geminal Diazide: Dimethylgermylene", *Organometallics* 1989, 8, 2606.
15. Barrau, J.; Balaji, V.; Michl, J. "Matrix Isolation and IR Spectroscopy of Germanethione  $\text{Me}_2\text{Ge-S}$ ", *Organometallics*, 1989, 8, 2034.
16. Radziszewski, J. G.; Michl, J. "Doubled Multiplexing in Fourier Transform Raman Spectroscopy", *J. Appl. Spectrosc.* 1990, 44, 414.
17. Michl, J., "The Relationship of Bonding to Electronic Spectra", *Acc. Chem. Res.* 1990, 23, 127.

C. Publications submitted since the last report was written:

18. Sun, Y.-P.; Miller, R. D.; Sooriyakumaran, R.; Michl, J. "Fluorescence of Poly(di-n-alkylsilane)s in Room-Temperature Solution", *J. Inorg. Organomet. Polym.*, in press.
19. McKinley, A. J.; Karatsu, T.; Wallraff, G. M.; Thompson, D. P.; Miller, R. D.; Michl, J. "Solution Photochemistry of Poly(di-n-alkylsilane)s. An EPR-ENDOR Study of the Structure of the Persistent Radicals", *J. Am. Chem. Soc.*, in press.
20. Davidson, I. M. T.; Michl, J.; Simpson, T., "The Photochemistry of Some Permethyloligosilanes", submitted for publication.
21. Michl, J.; Balaji, V., "Calculations of Photochemical Reactivity. Oligosilanes as an Illustration" in *Computational Advances in Organic Chemistry*; Ögretir, C., Csizmadia, I. G., Eds.; Kluwer: Dordrecht, The Netherlands; in press.
22. Balaji, V.; Michl, J. "Singlet Excitation in Polysilanes: *Ab initio* Calculations on Oligosilane Models", *Polyhedron*, in press.
23. Miller, R. D.; Michl, J. "Polysilane High Polymers", *Chem. Rev.* 1989, 89, 1359.
24. Miller, R. D.; Wallraff, G.; Clecak, N.; Sooriyakumaran, R.; Michl, J.; Karatsu, T.; McKinley, A. J.; Klingensmith, K. A.; Downing, J., "Polysilanes: Solution Photochemistry and Deep UV Lithography", *Polym. Eng. Sci.* 1989, 29, 882.

## SCIENTIFIC RESULTS

In this period, our work has emphasized oligosilanes and polysilanes, reflecting the intense interest in this area among chemists, physicists and material scientists. We have concentrated on the fundamental aspects (nos. 18-23 on the list of references) but participated also in the exploitation of these materials for deep UV lithography (no. 24 on the list).

We have performed a comprehensive study [18] of the luminescence of polysilanes in room-temperature solution and proposed an improved version of the chain segment model that we published in 1986. We have completed an extensive investigation [19] of the persistent radicals formed by UV irradiation of polysilane solutions and determined their structure, including conformational properties, by EPR, ENDOR, and TRIPLE resonance on a series of isotopically labeled polymers. These now probably are the best characterized polymer-based radicals of any kind. We have proposed plausible mechanisms for the complex chemical transformations involved in the formation of the observed radical products, and assigned a key role to photoinduced chain scission by homolysis and by reductive elimination; while the former had always been taken for granted, we postulated the latter only in 1989. We have now found confirming evidence for the latter from a study of the photochemistry of short-chain oligosilanes [20]. It has thus become clear that at least three primary processes are important in the photodegradation of polysilanes: the two types of chain scission, and the chain abridgement by silylene extrusion, described by Trefonas, West and Miller in 1985.

We have obtained satisfactory theoretical descriptions of all three primary processes by means of *ab initio* computations on model oligosilanes [21]. We have used this theoretical tool to investigate the excited electronic states in fair amount of detail [21, 22] and obtained a picture in which the photophysical and photochemical results dovetail. In particular, we have obtained evidence suggesting that a switch in the order of states occurs at chain lengths of about Si<sub>6</sub> to Si<sub>10</sub>. Shorter chains are believed to have a  $^1\sigma\pi^*$  state and the longer ones a  $^1\sigma\sigma^*$  state as the lowest excited singlets with obvious implications for spectroscopy, photophysics, and photochemistry. However, although reasonably advanced, the degree of understanding of these fascinating materials is still far from complete and the work is being continued. The current state of knowledge has been summarized in a comprehensive review [23].

In addition to results that have already been submitted for publication, further results are still being analyzed now. In particular, although some of the mysteries of the photophysics of oligosilanes have been resolved (e.g., what appeared to be a low-temperature conformational form of Si<sub>16</sub>Me<sub>34</sub> was demonstrated to be due to an aggregate which forms even in highly dilute solutions - true conformational effects have now also been found), several baffling observations remain to be explained, and in collaboration with Prof. West, we are continuing our efforts to understand simple model compounds such as Si<sub>16</sub>Me<sub>34</sub>.